



Technical Data

3649 Hempland Road
Lancaster, PA 17601-1393

Grade:	Aluminized Spun Bond
Type:	100% Spun Bond Polyester
Description:	Spun Bond with Atomized Aluminum for Static Control

US

Metric

Basis Weight

8.2 OZ / Sq. Yard

194 grams/sq. meter

Caliper

Overall Caliper

NA Inches

NA Millimeters

Corrugation Depth

NA Inches

NA Millimeters

Permeability/CFM

26 CFM/sq. ft.

216 L/sm/sec@ 20 mm WG

Mullen Burst

As is, Dry

287 Psi

1978 Kpa

Operating Temp.

250 Deg. F Continuous

Particle Efficiency by weight. Test Dust: AC Fine

0.5 micron 99.7%

1.0 micron 99.8%

2.0 micron 100%

Electrical

Conductivity

Less than 10⁶ OHM/Sq. when tested according to ASTM D257-99