



Grade:	Spun Bond with PTFE Membrane
Type:	Thermally Fused Polyester
Description:	8 OZ Polyester with PTFE Membrane Thermally Bonded

US

Metric

Basis Weight

8.5 OZ / Sq. Yard

201 grams/sq. meter

Caliper

Overall Caliper

NA Inches

NA Millimeters

Corrugation Depth

NA Inches

Millimeters

Permeability/CFM

7 CFM/sq. ft.

56.0 L/sm/sec@ 20 mm WG

Mullen Burst

As is, Dry

200 Psi Minimum

1378 Kpa

As is, Wet

Psi

Kpa

Continuous Operating

Temp.

275 Deg. F

135 Deg. C

Particle Efficiency by weight. Test Dust: AC Fine

0.3 micron

99.98%

0.5 micron

99.99%

1.0 micron

100%